

Application Data Sheet:

DENSIFY-K

CONCRETE HARDENER



APPLICATION:

- **ALWAYS TEST PRODUCT ON A SMALL AREA FIRST** and allow a 24 hour cure time to determine the ease of application and desired results for both stain resistance and appearance that will meet YOUR requirements.
- **CONCRETE MUST BE AT LEAST 30 DAYS OLD.**
- Ensure surfaces are clean and free from grout haze, dust, dirt and other residue.
- Wet area down with water in preparation for **DENSIFY-K**.

SEALING ANTI-DUSTING

- **DENSIFY-K** should be diluted with 2 parts water (depending on porosity of surface).
- Brush or mop solution into surface.
- Repeat step 2, allowing 24 hr intervals between each coating.
- Apply 3rd coat for OIL PROOFING with a 50/50 water/**DENSIFY-K** mix.
- Can be worked in with an industrial scrubbing machine and small amount of **NATURAL CLEAN** (100:1) to aid in penetration.

HARDENING – FLOOR POLISHING

- Ensure concrete has been ground with a 120 grit metal bond diamond pad.
- Using a soft broom apply **DENSIFY-K** and work into surface. (Depending on MPA of concrete you may require to add water i.e. 50/50 - Water/**DENSIFY-K** or use a small amount of **NATURAL CLEAN** 100:1 to aid in penetration)
- Repeat step 2, allowing 6 – 12 hours for **DENSIFY-K** to fully cure.
- Remove excess product with either a wet grind 100 grit resin bond pad or a 50 grit dry bond.

Disclaimer – User Guide

Solutions - Sealers for Stone & Tile believes the information contained in this document is accurate as **general advice only**. As general advice only it has been prepared without taking into account the objectives, problems or needs of the reader. Solutions – Sealers for Stone & Tile has presented this information as a guide only and accepts no liability for any loss or damage caused by any error in, or omission from, this document. Solutions – Sealers for Stone & Tile has no control over the use or misuse of this product, therefore no warranty expressed or implied shall be given. Solutions – Sealers obligations shall be limited to only replacing product PROVEN defective. The user **MUST** educate themselves on the performance value, application rates, substrate type and environment before product is applied, a **TEST** area is always highly recommended.

Technical Data Sheet:

DENSIFY-K

CONCRETE HARDNER



Description:

DENSIFY-K is a concrete densifier for sealing, grinding and protection. **DENSIFY-K** can be used for sealing warehouse floors, shopping centre car parks, heavy pedestrian & traffic areas.

Advantages:

- Unlike other concrete densifiers, **DENSIFY-K** will not turn concrete yellow, discolour, chip, peel or show unsightly wear patterns with use.
 - Will not tyre mark
 - Increases the wear surface strength
 - Penetrates the concrete surface to seal, densify & waterproof.
-

Characteristics:

Colour:	Clear
Weight	1.7
Solvent	Water
DG Class	Non DG
Coverage	10 - 15 sq m per lt (depending on porosity)

Recommendations:

Use on concrete floors including sealing warehouse floors, shopping centre car parks, heavy pedestrian & traffic areas.

Disclaimer – User Guide

*Solutions - Sealers for Stone & Tile believes the information contained in this document is accurate as **general advice only**. As general advice only it has been prepared without taking into account the objectives, problems or needs of the reader. Solutions – Sealers for Stone & Tile has presented this information as a guide only and accepts no liability for any loss or damage caused by any error in, or omission from, this document. Solutions – Sealers for Stone & Tile has no control over the use or misuse of this product, therefore no warranty expressed or implied shall be given. Solutions – Sealers obligations shall be limited to only replacing product PROVEN defective. The user MUST educate themselves on the performance value, application rates, substrate type and environment before product is applied, a TEST area is always highly recommended.*

