

# PRODUCT DATA SHEET

## Sika® WT-200 P

### Water Resisting and Crystalline Waterproofing Concrete Admixture

#### DESCRIPTION

Sika® WT-200 P is a combined water resisting and crystalline waterproofing admixture used to reduce the permeability of concrete and to enhance the self-healing abilities of the concrete.

#### USES

Sika® WT-200 P has been specifically formulated to produce high quality waterproof concrete. Sika® WT-200 P treated concrete is used as a part of the Sika® Watertight Concrete System.

Sika® WT-200 P can be used in any below / in / above ground watertight structures such as:

- Basements
- Parking garages
- Utility / plant rooms
- Tunnels
- Swimming pools
- Water retaining structures
- Dams
- Waste water treatment structures
- Underground commercial facilities (malls, transportation hubs etc.)

#### CHARACTERISTICS / ADVANTAGES

Sika® WT-200 P consists of a mixture of cements, amino alcohols and fillers. These active materials will form non-soluble materials throughout the pore and capillary structure of the concrete and seal the concrete permanently against penetration of water and other liquids. In addition the special formula and ingredients of Sika® WT-200 P enhances the self-healing properties of concrete and will improve the ability to heal cracks in concrete.

Sika® WT-200 P has the following characteristics and benefits:

- Reduced water penetration under pressure
- Reduced water absorption
- Enhancement of self-healing properties of the concrete
- Improvement in resistance against chemical attack
- Reduced vapour transmission
- Higher compressive strength

#### APPROVALS / CERTIFICATES

Conforms to the requirements of AS1478.1 , type Special Purpose normal setting

Sika® WT-200 P is approved for potable water use (AS4020-2005)

#### PRODUCT INFORMATION

<b>Composition</b>	Mixture of cements, amino alcohols and fillers
<b>Packaging</b>	1.75 kg pulpable bags (6 bags/sealed plastic bucket)
<b>Shelf life</b>	12 months from date of production if stored in unopened and undamaged original sealed containers.
<b>Storage conditions</b>	Storage at temperatures between 5 °C and 35 °C. Protect from direct sunlight, moisture, frost and contamination.
<b>Appearance and colour</b>	Grayish powder

## TECHNICAL INFORMATION

<b>Concreting guidance</b>	The standard rules of good concreting practice, concerning production and placing, are to be followed. Laboratory trials shall be carried out before concreting on site, especially when using a new mix design or producing new concrete components. Fresh concrete must be cured properly and curing applied as early as possible.
<b>Concrete mix design</b>	<ul style="list-style-type: none"> <li>▪ For waterproof concrete: Concrete mix design depends on local requirements and / or local standards for watertight concrete systems.</li> <li>▪ For Sika® Watertight Concrete: Sika® WT-200 P has been formulated for use in concrete with a minimum binder content of 350 kg/m<sup>3</sup> and a maximum w/b-ratio of 0.45. Depending on the specific mix design the dosage of HRW /superplasticizer has to be evaluated in order to achieve a consistency <math>\geq 110</math> mm (slump test AS1012.3.1)</li> <li>▪ Laboratory trials are always recommended to evaluate and confirm actual water reduction and consistency class.</li> </ul>
<b>Effect on setting</b>	The chemical and physical composition of the components, concrete, Sika® WT-200 P and concrete and ambient temperature can affect the setting time of the concrete.

## APPLICATION INFORMATION

<b>Recommended dosage</b>	1–2 % of Sika® WT-200 P by weight of binder
<b>Dispensing</b>	<p>Sika® WT-200 P is added at the time of batching to the concrete. Depending on the operation it can be dosed</p> <ul style="list-style-type: none"> <li>▪ At the dry batching plant : add Sika® WT-200 P either to the gauging / mixing water to form a very thin slurry and add it into the truck barrel or load it along with the concrete components. Then mix thoroughly for about 60 seconds/m<sup>3</sup>. Do not add Sika® WT-200 P to wet concrete.</li> <li>▪ At the wet batching plant (mixer) : dispense Sika® WT-200 P and the concrete components together, mixing as per the internal production procedures.</li> </ul> <p>The w/b-ratio and consistency control remains the responsibility of the concrete producer.</p>
<b>Compatibility</b>	<p>Sika® WT-200 P may be combined with many other Sika products.</p> <p>Note: Always conduct trials before combining products in specific mixes and contact Sika technical service for more information and advice.</p>

## BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

## IMPORTANT CONSIDERATIONS

When using Sika® WT-200 P a suitable mix design has to be taken into account and local material sources shall be tested.

## ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) con-

taining physical, ecological, toxicological and other safety-related data.

## LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the declared data for this product may vary from country to country. Please consult the local Product Data Sheet for the exact product data.

## LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

**Sika Australia Pty Limited**

ABN 12 001 342 329

aus.sika.com

Tel: 1300 22 33 48

**Product Data Sheet**

Sika® WT-200 P

April 2023, Version 01.04

021403011000000094

