

Technical Data Sheet ISSUED MARCH 2026

PRODUCT DESCRIPTION

WPA ATC is an economic, aliphatic, single component, liquid applied, moisture cured, polyurethane coating. It has been formulated as a complementary topcoat for WPA 3400, WPA 3480 and WPA 992UV membranes. WPA ATC offers protection from degradation of the waterproofing membrane due to UV exposure.

Recommended for:

- Rooftops
- Plant Rooms
- Car Parks
- Polyurea Membranes
- Polyurethane Membranes

FEATURES AND BENEFITS

- UV Stable
- Excellent weatherability
- Good colour retention
- Fast curing

APPLICATION PROCEDURE

Mixing

Before application, mix WPA ATC using a mechanical mixer at slow speed. If required, add WPA ATC Catalyst and continue mixing until a homogeneous mixture and colour is attained. Boxing of the material is recommended. Use caution not to

whip air into the material as this may result in pinhole blisters and/or shortened pot life. Do not mix in an up and down motion.

Application

For best results, use a squeegee. Airless sprayer or phenolic resin core roller may be used but extra care should be taken not to cause air bubbles.

Apply in a continuous coating to minimise lines and/or streaking.

Curing

At 24°C and 50% relative humidity, allow each coat to cure 16 hours. Cure time will vary depending on temperature and humidity.

Allow 24 hours before permitting light pedestrian traffic and at least 72 hours before permitting heavy pedestrian or vehicular traffic on the finished surface.

Uncured WPA ATC is very sensitive to heat and moisture. Higher temperatures and/or high humidity will accelerate the cure time. Use caution in batch sizes and thickness of application.

Low temperature and/or low humidity extend the cure time.

If accelerated curing is required, add 0.95 litre of WPA ATC Catalyst to 18.9 litres of WPA ATC and mix thoroughly. This accelerated WPA ATC will cure in 6-8 hours at 24°C and 50% relative humidity.

WPA ATC System Structure	UV Stable Coating	Light Pedestrian Traffic / Service Traffic	Heavy Pedestrian Traffic	Vehicular Traffic system
Primer: WPA 3460	50-150 g/M ²	50-150 g/M ²	50-150 g/M ²	50-150 g/M ²
Membrane: WPA 3400	1.65 kg (1.5 litre) of WPA 3400 will cover approximately 1 M ² at 1.5 mm coating thickness.	1.65 kg (1.5 litre) of WPA 3400 will cover approximately 1M ² at 1.5 mm coating thickness.	1.65 kg (1.5 litre) of WPA 3400 will cover approximately 1M ² at 1.5 mm coating thickness.	2mm minimum thickness. 2.2 kg (2 litre) of WPA 3400 will cover approximately 1M ² at 2 mm coating thickness.
Wear Coat / Isolation layer: WPA ATC	N/A	N/A	0.41 litre/M ²	0.41 litre/M ²
Aggregate	N/A	WPA Alox - 3 kilo bag mixed into 18.9L drum of WPA ATC and rolled out. Or Broadcast and back rolled into WPA ATC	WPA Alox / Kiln Dried sand broadcast into the WPA ATC to refusal.	WPA Alox / Kiln Dried sand broadcast into the WPA ATC to refusal.
UV Stable Top Coat: WPA ATC	0.31 litre/M ²	0.31 litre/M ²	0.41 litre/M ²	0.41 litre/M ²
Turning Circle / 3rd Coat	N/A	N/A	N/A	3rd coat + Alox on turning circles and ramps. 0.41 litre/M ²

Technical Data Sheet ISSUED MARCH 2026

If WPA ATC Catalyst is used to accelerate curing, then recoat window for the subsequent coat is reduced to 24 hours after cure. If the recoat window has passed, then solvent wipe the surface with VOC-compliant solvent and re-prime surface.

Clean Up

Equipment should be cleaned with an environmentally safe solvent, as permitted under local regulations, immediately after use.

Storage

WPA ATC has a shelf life of 1 year from date of manufacture in original, factory-sealed containers when stored indoors at a temperature between 15-35°C.

LIMITATIONS

Do not apply **WPA ATC**:

- Over damp, wet or contaminated substrates;
- If it is raining or if rain is imminent;
- To areas subject to negative hydrostatic pressure or rising damp.
- At temperatures above 35°C.

BEWARE OF CONDENSATION!

The substrate temperature must be at least 3°C above dew point to reduce the risk of de-lamination due to condensation.

Packaging

- 18.9 Litre drum

SAFETY INSTRUCTIONS

For instructions on the safe use of WPA ATC please refer to the latest version of the Safety Data Sheet available from our

website www.wpa-us.com.au.

WARRANTY CONDITIONS

Bayset Pty Ltd trading as Waterproofing Products Australia (Bayset) offers a limited warranty in respect of this product, subject to certain terms and conditions set out in the warranty documentation which has been made available at www.bayset.com.au. Please contact Bayset directly to obtain a copy of the warranty documentation relevant to this product.

DISCLAIMER

The technical information and application advice given in this Technical Data Sheet is based on the present state of Bayset Pty Ltd's best scientific and practical knowledge and is intended to give a fair description of the product and its capabilities. As the information contained herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness, either expressed or implied, is given other than those required by law. In practice, the substrate and environmental conditions vary widely, making it essential for the user to determine the product's suitability for a particular application and that the product is not used beyond its physical limitations.

The user is responsible for checking the suitability of products for their intended use.

*NOTE

Field service where provided does not constitute supervisory responsibility. Suggestions made by Bayset Pty Ltd (trading as Waterproofing Products Australia) either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not Waterproofing Products Australia, are responsible for carrying out procedures appropriate to a specific application.

DOCUMENT CONTROL	
Product	WPA ATC
Initial Issue	October 2020
Technical Amendment	March 2026
Author	SR

Technical Data Sheets are subject to change without notice. For latest revision, check our website at www.wpa-us.com.au

This is a CONTROLLED document under WPA's Quality System.